

SOLID RL 685

RL 685 WATER BASED ACRYLIC FLOOR

SOLID RL 685 TANIM

SOLID RL 685 acrylic resin based, water based, breathable, highly resistant to external conditions, tennis court transition primer. It is designed for tennis courts, basketball and volleyball courts.

FEATURES

SOLID RL 685, It is an acrylic resin based, water based, breathable, highly resistant to external conditions, court paint. It is designed for tennis courts and can also be used safely in basketball, volleyball and similar field applications..

SOLID RL 685 acrylic resin based water based transition primer used before tennis court coating.

General Features

- High alkali resistance
- Low water absorption
- Breathable
- Flexible
- Completely prevents dusting on the floor

AREA OF USE

SOLID RL 685, It can be used safely on all amateur and professional tennis courts before application on asphalt and concrete.

SURFACE PREPARATION

Asphalt Resurefaer :

Old Asphalt Resurefaer : The surface is cleaned from dust, dirt and foreign materials. If the surfaces to be repaired are to be repaired with fresh asphalt, the sub-surface is heated with a blowtorch and fused with the hot asphalt to be applied on it. Following the complete drying of the repaired surface, capillary washing is performed with 6 bar pressure water.

New Asphalt Resurefaer Before the new asphalt surface is prepared, the substrate must first be compacted with 5% moisture content.

The surface should be levelled with filler material. Following the surface correction process, coating with Geotextil before asphalt is done. If the geotextile surface is risky, 120 gr/m², if not, 80 gr/m² is applied. Asphalt after geotextile application application is made and the necessary slope is given in accordance with the standards. Full drying after asphalt application for 14 days. After waiting, the surface is capillary washed with 6 bar pressurised water to remove accumulated dirt and foreign materials.

Concrete Surface:

The surface is cleaned from dust, dirt and foreign substances. If the surfaces to be repaired require high filling, they are repaired with SOLID WET 365..

SOLID RL 685

RL 685 WATER BASED ACRYLIC FLOOR

APPLICATION METHOD

SOLID RL 685, It is applied with a roller or rake on a previously prepared surface according to the application detail and order..

PACKAGING AND STORAGE

SOLID RL 685 It is available in plastic barrels of kg and plastic buckets of 50 kg. The material should be stored in a dry environment and protected from the adverse effects of sun, rain, extreme heat and cold weather. It can be stored for 12 months in unopened packages.

ENVIRONMENTAL CONDITIONS

Ambient temperature should be between +15°C and 35°C. Do not apply when the relative humidity exceeds 80%. The surface temperature must be at least 3-5 °C above the dew point to avoid surface condensation..

It should be known that the consumption will increase in the application to be made at low temperatures. Surface temperature at least +5°C to a maximum of 45°C high.

*Our information about the products has been prepared on the basis of our own laboratory trials and researches under normal conditions. Our company is not responsible for studies under unsuitable application conditions. The right to change this information is reserved by our company. For more detailed information, please contact R.Y.K.

Rev. No:09/Rev.Date: October 2022



Solid Epoxy Flooring Systems

287 Crooks Ave, Clifton, NJ 07011
+1 (973) 449-3616
solidepoxyfloor@gmail.com
<https://solidepoxyflooring.com>